

SP 106

MULTI-PURPOSE EPOXY SYSTEM

- **Use for gluing, coatings, laminating and filling**
- **Rapid curing, even at low temperatures**
- **Simple to use**

INTRODUCTION

SP 106 is a simple to use, all-purpose epoxy which can be used for gluing, coating, laminating and filling. With its range of hardeners, and easy 5:1 mix ratio by volume, SP 106 provides a quick and convenient way of using one epoxy system for a very wide range of tasks. SP 106 has been established for over 20 years as the primary epoxy system for the manufacture and repair of wooden boats, and it is now widely used in many other woodworking applications from cabinet making to the manufacture of large wooden moulds. With its Extra Slow Hardener SP 106 can be used for jobs requiring a long working time, or in 'tropical' conditions of high ambient temperatures.

In its unmodified form, SP 106 can be used as a clear coating for wood and other substrates, or for laminating lightweight glassfibre fabrics such as those used for reinforcing joints. When used for clear coating, cured SP 106 should be overcoated with a UV-resistant varnish.

By using the Gurit range of filler powders, an SP 106 resin and hardener mix can be turned into a very effective adhesive or filling compound. Details of this filler range, and how to use them, are contained in a separate information sheet (Filler Guide) and typical filling and fairing mixes (resin / hardener / filler) are shown in this data sheet.

INSTRUCTIONS FOR USE

WORKSHOP CONDITIONS

SP 106 should be used at between 15°C-25°C. At lower temperatures the product thickens and therefore it is necessary to prewarm resin, hardener and surfaces to be bonded or coated before use. At higher temperatures and larger volumes the pot life of the mixed resin/hardener is reduced.

MIXING AND HANDLING

Use either Fast, Slow or Extra Slow hardener, depending on the speed of reaction and working time required, in the ratio:

SP 106 resin	SP 106 hardener
5 : 1 (by volume)	
100 : 18 (by weight)	

Mix as accurately as possible since varying the amount of hardener will not change the cure speed significantly but will greatly reduce the cured strength and water resistance properties of the material.

If using the Gurit pump dispensing system ensure that the pumps are fitted and used according to the pump pack instructions. Pumps should also be regularly checked and cleaned to ensure that they continue to dispense the correct volumes.

Solvent-free epoxies have limited pot life. Mix sufficient only for immediate use to avoid excessive heat build up and resin wastage through early gelation: with **fast** hardener mix no more than can be used in 5-10 minutes; with **slow and extra slow** hardener mix no more than can be used in 15 - 20 minutes.

MIXING RESIN & HARDENER

The SP 106 resin and hardener should be mixed thoroughly together for at least one minute. To maximise the working life, use from the pot quickly or transfer to a shallow tray to help dissipate the heat of the reaction. See table on "Working Properties".

SURFACE PREPARATION

Before using the product ensure that surfaces to be bonded, coated or filled are clean, dry and dust-free. All surfaces should be prepared by abrading with medium grit paper, the dust removed then wiped with Gurit Fast Epoxy Solvent (Solvent A) for maximum adhesion.

USAGE

GLUING

SP 106 is a most effective glue for bonding wood, metals, stone, concrete and grp. To enhance gap-filling properties and prevent glue-starved joints, the appropriate filler powders should be added to the mixed resin/hardener to make a 'thicker' mix (see table on adhesive mixes).

FILLET BONDING

Constructing radiused fillet joints using epoxy plus fillers is a convenient and economical method of bonding together plywood panels which meet at an angle. Use either **low density** (glass bubbles or microballoons + colloidal silica) or **high density** (microfibres + colloidal silica) filler mixes depending on use and strength required.

High density mixes are used in structural applications where highest strength is required. Strength is also determined by the radius of the fillet = (2.5 to 3 x thickness of plywood for high density fillet, 5 to 6 x plywood thickness for low density fillet).

COATING

With a minimum of 450 microns coating thickness, SP 106 forms an effective water resistant seal on wood. On flat surfaces this can be achieved in one or two coats (the latter allowing a better surface finish) but on inclined or vertical surfaces multiple thinner coats will be required. It is possible to overcoat when the first coat is still 'tacky' for a rapid build-up (see table "Working Properties"). However, if the epoxy is allowed to cure beyond this tacky state, the coating must be sanded **thoroughly**, preferably using wet abrasive paper, and dry thoroughly before reapplying another epoxy coat or paint system. If the coating is allowed to cure at the lower end of the temperature range, or if the ambient humidity is moderate to high, a greasy surface 'by-product' may form. This is quite normal and should be removed using warm soapy water and a Scotchbrite pad, or Gurit Cleaning Fluid (Solvent C).

PIGMENTING

Use Gurit epoxy pigments up to 10% by volume (white, grey, black available). Add the pigment to the SP 106 resin component and then to this volume of SP 106 / pigmented resin add the hardener at 5:1 ratio by volume.

WOOD STAINING

Only water-based wood stains should be used. Do not use spirit or oil-based stains or preservatives.

FIBRE REINFORCEMENT

Use SP 106 epoxy with glass, carbon or aramid fabrics as a low cost laminating resin for composite components, sheathing wood, or repairs to grp.

USING FILLER POWDERS

Filler powders control the working properties of the resin mix and are beneficial for almost all bonding operations to give additional gap-filling properties and extend the glue quantity. Fillers are also used for fillet bonding and to create low cost, low density epoxy fairing mixes. When using fillers always mix the resin and hardener first and then stir in the appropriate filler(s) in the correct quantity, as shown in the tables.

FILLING AND FAIRING MIXES

Description of Mix	Filler Type	Ease of Sanding of Mix	Water Resistance of Mix	Filler Quantity (% by Wt. of R/H Mix)	Filler Quantity (for 1kg R/H Mix)	Silica Addition (% by Wt. of R/H Mix)	Silica Addition (for 1kg R/H Mix)	Approx. Density of Mix	Approx. Vol. of Filler Mix from 1kg R/H Mix
Brown, low density	Microballoons	Easy	Moderate	25-30%	250-300g	2-3%	20-30g	0.6g/cm ³	2.2 litres
White, low density	Glass Bubbles	Moderate	High	35-40%	350-400g	3-5%	30-50g	0.5g/cm ³	3 litres

ADHESIVE MIXES

Description of Mix	Filler Type	Filler Quantity (% by Wt. of R/H Mix)	Filler Quantity (for 1kg R/H Mix)	Silica Addition (% by Wt. of R/H Mix)	Silica Addition (for 1kg R/H Mix)	Approx. Density of Mix	Approx. Vol. of Filler Mix from 1kg R/H Mix
Brown, low density	Microballoons *	15-20%	150-200g	4-5%	40-50g	0.7g/cm ³	1.8 litres
White, low density	Glass Bubbles *	15-20%	150-200g	5-6%	50-60g	0.6g/cm ³	2 litres
Opaque, high strength	Microfibres	7-10%	70-100g	3-4%	30-40g	0.9g/cm ³	1.1 litres

Notes: All filler additions are approximate and can be adjusted by the user to achieve the desired consistency.

*Microfibres are always preferred for load-carrying adhesive joints.

COVERAGE

Thickness (per coat)	50-150 microns*
Coating coverage (@ 0.15mm)	Approx. 7m ² /litre**
Glue coverage	Approx. 3-4m ² /litre**

* Depending on temperature and surface inclination.

** Depends on surface porosity and evenness.

For further information, see the Filler Guide.

PROPERTIES

Component Properties				
	Resin	Fast Hardener	Slow Hardener	Extra Slow Hardener
Mix Ratio (by weight)	100	18	18	18
Mix Ratio (by volume)	100	20	20	20
Viscosity @ 15°C (cP)	2180	344	143	908
Viscosity @ 20°C (cP)	1360	263	106	594
Viscosity @ 25°C (cP)	815	198	74	394
Viscosity @ 30°C (cP)	525	153	54	258
Shelf Life (months)	24	24	24	24
Colour (Gardner)	1	4*	3*	>8
Mixed Colour (Gardner)	-	1	1	8
Component Density (g/cm ³)	1.164	1.008	0.968	0.979
Mixed Density (g/cm ³)	-	1.138	1.131	1.125
Hazard Definition	Please refer to SDS			

Cured System Properties			
	Cured (28 days @ 21°C)		
	Fast	Slow	Extra Slow
Tg DMTA (Peak Tan δ)(°C)	61.8	64.8	73.8
Tg Ult - DMTA (°C)	80.1	82.9	86.1
ΔH - DSC (J/g)	2	13	-
Tg1 - DMTA (°C)	51.6	53.7	61.5
Moisture Absorp. (%)	1.991	1.578	-
Cured Density (g/cm ³)	1.191	1.188	1.175
Linear Shrinkage (%)	1.6	1.7	1.6
Barcol Hardness	26	30	24
Yellowing Index (ΔYI)	42	-	-
Shear Strength on Steel (MPa)	14.67	15.67	17.33
Shear Strength Wet Retention (%)	89	76	-

*Material darkens on storage. **After removal of any surface-by-product. ††SP 106 mixes with these hardeners are not recommended for use as coatings at this temperature.

Notes: For an explanation of test methods used see 'Formulated Products Technical Characteristics'.

All figures quoted are indicative of the properties of the product concerned. Some batch to batch variation may occur.

† All times are measured from when resin and hardener are first mixed together.

PROPERTIES (CONT'D)

Working Properties vs Temperature												
	Resin / Fast Hardener				Resin / Slow Hardener				Resin / Extra Slow Hardener			
	15°C	20°C	25°C	30°C	15°C	20°C	25°C	30°C	15°C	20°C	25°C	30°C
Initial Mixed Viscosity (cP)	2770	1870	1263	844	2181	1366	862	545	2872	1826	1149	720
†Gel Time - 150g Mix in Water (hrs:mins)	-	0:17	-	0:12	-	0:31	-	0:16	-	0:51	-	0:21
†Pot Life - 500g Mix in Air (hrs:mins)	-	0:15	-	0:10	-	0:19	-	0:13	-	0:34	-	0:14
†Working Time (hrs:mins)	2:20	1:05	0:30	0:13	3:00	2:20	1:50	1:30	4:10	3:10	2:20	1:50
†Tack Off Time (hrs:mins)	3:30	1:30	0:45	0:21	- ††	3:50	2:50	2:10	- ††	5:00	3:40	2:45
†Latest Overcoating Time (hrs:mins)	2:15	2:15	1:25	0:50	- ††	5:20	3:50	2:45	- ††	4:00	3:00	2:15
†Clamp Time (hrs:mins)	4:20	3:15	2:25	1:45	7:10	5:00	3:10	2:20	8:40	6:25	4:50	3:30
†Earliest Sanding Time (hrs)**	20	15	11	8½	26	19	14½	11	31	23	17	13







*Material darkens on storage. **After removal of any surface-by-product. ††SP 106 mixes with these hardeners are not recommended for use as coatings at this temperature.

Notes: For an explanation of test methods used see 'Formulated Products Technical Characteristics'.

All figures quoted are indicative of the properties of the product concerned. Some batch to batch variation may occur.

† All times are measured from when resin and hardener are first mixed together.

MECHANICAL PROPERTIES



*After removal of any surface-by-product.

Notes: For an explanation of test methods used see 'Formulated Products Technical Characteristics'.

All figures quoted are indicative of the properties of the product concerned. Some batch to batch variation may occur.

† All times are measured from when resin and hardener are first mixed together.

HEALTH AND SAFETY

The following points must be considered:

1. Skin contact must be avoided by wearing protective gloves. Gurit recommends the use of disposable nitrile gloves for most applications. The use of barrier creams is not recommended, but to preserve skin condition a moisturising cream should be used after washing.
2. Overalls or other protective clothing should be worn when mixing, laminating or sanding. Contaminated work clothes should be thoroughly cleaned before re-use.
3. Eye protection should be worn if there is a risk of resin, hardener, solvent or dust entering the eyes. If this occurs flush the eye with water for 15 minutes, holding the eyelid open, and seek medical attention.
4. Ensure adequate ventilation in work areas. Respiratory protection should be worn if there is insufficient ventilation. Solvent vapours should not be inhaled as they can cause dizziness, headaches, loss of consciousness and can have long term health effects.
5. If the skin becomes contaminated, then the area must be immediately cleansed. The use of resin-removing cleansers is recommended. To finish, wash with soap and warm water. The use of solvents on the skin to remove resins etc must be avoided.

Washing should be part of routine practice:

- before eating or drinking
- before smoking
- before using the lavatory
- after finishing work

6. The inhalation of sanding dust should be avoided and if it settles on the skin then it should be washed off. After more extensive sanding operations a shower/bath and hair wash is advised.

Gurit produces a separate full Safety Data Sheet for all hazardous products. Please ensure that you have the correct SDS to hand for the materials you are using before commencing work. A more detailed guide for the safe use of Gurit resin systems is also available from Gurit, and can be found at www.gurit.com

APPLICABLE RISK & SAFETY PHRASES

Please refer to product SDS for up to date information specific to this product.

TRANSPORT & STORAGE

The resin and hardeners should be kept in securely closed containers during transport and storage.

Storage should be in a warm dry place out of direct sunlight and protected from frost. The temperature should be between 10°C and 25°C. Containers should be firmly closed. Hardeners, in particular, will suffer serious degradation if left exposed to air.

NOTICE

All advice, instruction or recommendation is given in good faith but the selling Gurit entity (the Company) only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at Gurit's Website: www.gurit.com/terms-and-conditions.aspx

The Company strongly recommends that Customers make test panels in the final process conditions and conduct appropriate testing of any goods or materials supplied by the Company prior to final use to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. Due to the varied nature of end-use applications, the Company does, in particular, not warrant that the test panels in the final process conditions and/or the final component pass any fire standards.

The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

Gurit is continuously reviewing and updating literature. Please ensure that you have the current version by contacting your sales contact and quoting the revision number in the bottom left-hand corner of this page.

TECHNICAL CONTACT INFORMATION

For all other enquiries such as technical queries:

Telephone + 44 1983 828000 (08:30 – 17:00 GMT)

Email technical.support@gurit.com

24-HOUR CHEMICAL EMERGENCY NUMBER

For advice on chemical emergencies, spillages, fires or exposures:

Europe +44 1273 289451

Americas +1 646 844 7309

APAC +65 3158 1412

E customer.support@gurit.com

W www.gurit.com